Claims

1. Process for producing HT foams for further processing into sandwich materials, ~~characterized in that~~wherein particles of a high-temperature polymer are foamed and sintered in a mould at a sintering temperature T_1 to form an HT foam moulding and subsequently the mould cavity is heated to a temperature T_2 at least 10°C above the sintering temperature and not more than 20°C above the glass transition temperature of the HT polymer for 5 to 120 sec, and wherein the sintering temperature T_1 of the HT polymer is between 140°C and 220°C, the glass transition temperature of the HT polymer is between 210°C and 235°C and temperature T_2 is between 180°C and 255°C.

~~2. Process according to Claim 1, characterized in that the sintering temperature T_1 of the HT polymer is between 140°C and 220°C, the glass transition temperature of the HT polymer is between 210°C and 235°C and temperature T_2 is between 180°C and 255°C.~~

~~3.~~2. Process according to Claim ~~2, characterized in that~~1, wherein the sintering temperature T_1 of the HT polymer is between 145°C and 180°C, the glass transition temperature of the HT polymer is between 215°C and 230°C and temperature T_2 is between 190°C and 240°C.

~~4.~~3. Process according to any of Claims 1 to ~~3, characterized in that~~2, wherein the mould cavity is heated to a temperature T_2 for 15 to 90 sec.

~~5.~~4. Process according to any of Claims 1 to ~~4, characterized in that~~3, wherein the HT polymer is ~~polyethersulfone (PESU~~polyetherimide (PEI).

~~6. Process according to any of Claims 1 to 4, characterized in that the HT polymer is polyphenylsulfone (PPSU).~~

~~7. Process according to any of Claims 1 to 4, characterized in that the HT polymer is polyetherimide (PEI).~~

~~8.~~5. ~~Process according to any of Claims 1 to 8, characterized in that~~wherein the particles of the high-temperature polymer are foamed in the mould to form the HT foam moulding at the sintering temperature T_1 between 140°C and 180°C in such a way that upon heating of the mould cavity to the temperature T_2 at least 5% by weight of the originally employed blowing agent still remains in the material.

~~9.~~6. Process according to any of Claims 1 to ~~8, characterized in that~~5, wherein the mould cavity is heated to a temperature T_2 which is at least 15°C above the sintering temperature and below the glass transition temperature of the HT polymer for 5 to 120 sec.

~~10.~~7. Process according to any of claims 1 to ~~9, characterized in that~~6, wherein prior to foaming the mould is filled with non-prefoamed HT polymer particles having a particle size between 0.5 and 5.0 mm.

~~11.~~8. Process according to any of claims 1 to ~~9, characterized in that~~6, wherein prior to foaming the mould is filled with prefoamed HT polymer particles having a maximum particle size between 1.0 and 10 mm and a bulk density of 30 to 200 kg/m^3.