

APPLICANTS:

SOMAR CORPORATION

TITLE:

EPOXY POWDER COATING COMPOSITION
FOR USE IN ELECTROSTATIC COATING

AGENTS:

LLOYD WISE, TREGEAR & CO
Norman House
105-109 Strand
LONDON. WC2R OAE
United Kingdom

REF:

PCA-35640

REPLACED SHEETS		SG
☒	Description : paged 1 to paged 11	
☒	Claim(s) : paged 1/2 to paged 7/2	
☐	Drawing(s) : paged to paged	
☒	Abstract : paged 1/4 to paged	
DATE OF RECEIPT		

This invention relates to a powder coating composition suitable for use in electrostatic coating.

Electrostatic coating is now used in various fields because of a lot of advantages thereof such as easiness in
5 controlling the thickness of coatings and absence of a step of preheating articles to be coated. Thus, a number of powder coating compositions are commercially available for use in electrostatic coating processes. Known powder coating
10 compositions, however, has a problem because it is difficult to obtain thick coatings having a smooth surface. Namely, when a coating having a thickness of 250 μm or more is to be formed, particles of the coating composition cause electrostatic repelling so that the surface of the resulting coating becomes non-uniform.

15 The present invention has been made with the foregoing problem in conventional powder coating compositions in view. In accordance with one aspect of the present invention there is provided a powder coating composition comprising a particulate material consisting of particles having a particle size in the
20 range of 3-180 μm and a volume resistivity of at least 10^7 ohm·cm and each containing an epoxy resin and a curing agent for the epoxy resin, and a charge controlling agent selected from the group consisting of an acrylic resin having an average particle size in the range of 0.05-1 μm and silica whose primary
25 particles having an average particle size in the range of 2-500 nm, the amount of said charge controlling agent being 0.01-5 % based on the total weight of said particulate material and said charge controlling agent, and said charge controlling agent being present on surfaces of said particles of said particulate
30 material.

In another aspect, the present invention provides a powder coating composition comprising:

a first particulate material consisting of first particles having a particle size in the range of 3-180 μm and a
35 volume resistivity of at least 10^7 ohm·cm and each containing a first epoxy resin and a first curing agent for the first epoxy resin;





a second particulate material consisting of second particles having a particle size in the range of 3-180 μm and a volume resistivity of at least 10^7 ohm $\cdot$ cm and each containing a second epoxy resin and a second curing agent for the second epoxy resin;

a first, particulate, charge controlling agent depositing on surfaces of said first particulate material; and

a second, particulate, charge controlling agent depositing on surfaces of said second particulate material, said first and second charge controlling agent differing in static characteristics.

The present invention will now be described in detail below.

15 First Embodiment:

The powder coating composition of the first embodiment according to the present invention is composed of a particulate material consisting of particles having a particle size in the range of 3-180 μm and a volume resistivity of at least 10^7 ohm $\cdot$ cm. Each of the particles contains an epoxy resin and a curing agent for the epoxy resin.

Any conventionally used epoxy resin may be used in the present invention. Examples of suitable epoxy resins include glycidyl ethers of bisphenol A, bisphenol S, bisphenol F, phenol novolak resins and cresol novolak resins; glycidyl ester epoxy resins; glycidyl amino epoxy resins; cycloaliphatic epoxy resins; linear aliphatic epoxy resins; heterocyclic epoxy resins; and halogenated epoxy resins. These epoxy resins may be used singly or as a mixture of two or more. Epoxy resins which are solid at 20 ° C are generally used. But, it is possible to use the solid epoxy resins in conjunction with liquid epoxy resins as long as the mixed epoxy resins are solid at 20 ° C.

Conventional curing agents may be used for the above epoxy resins. Illustrative of suitable curing agents are aromatic amines, acid anhydrides, guanidine compounds such as dicyandiamide, and imidazole compounds.

In addition to the epoxy resin and the curing agent,



the particulate material may further contain a filler, a pigment or the like conventional additive.

The particulate material is blended, in a dry state using, for example, a Henschel mixer or a Nauta mixer, with a charge controlling agent selected from an acrylic resin having an average particle size in the range of 0.05-1 μ m, preferably 0.15-0.6 μ m and silica whose primary particles having an average particle size in the range of 2-500 nm, preferably 5-100 nm so that the charge control agent deposits on the surface of the particles of the particulate material. The amount of the charge controlling agent is 0.01-5 % based on the total weight of the particulate material and the charge controlling agent.

The acrylic resin to be used as the charge controlling agent is a homopolymer or a copolymer of an alkyl ester of acrylic or methacrylic acid. Polymethyl methacrylates and polymethyl acrylates are examples of suitable acrylic resins.

When frictionally contacted with iron powder, acrylic resins are either positively or negatively charged. Both of the positively and negatively chargeable acrylic resins may be used for the purpose of the present invention. In this case, it is preferred that the negatively chargeable acrylic resins or a mixture of the negatively chargeable and positively chargeable acrylic resins be used in combination with the particulate material which is good in chargeability. In the case of the particulate material which is relatively poor in chargeability, then it is preferred that the particulate material be used in combination with the positively chargeable acrylic resins or a mixture of the positively chargeable and positively chargeable acrylic resins. The mixing ratio of the positively chargeable acrylic resin to the negatively chargeable acrylic resin is selected so as to obtain optimum results according to the chargeability of the particulate material.

The ratings of "good" and "poor" in the chargeability of the particulate material are determined by as follows:

Sample particulate material is discharged through a nozzle of an electrostatic coating gun (Model AH-1 manufactured by Nordson Inc.) with an air pressure for discharging the particulate



material of 1.5 kg/cm^2 and an air pressure for accelerating the particulate material of 3.5 kg/cm^2 while measuring the charge by means of a charge meter equipped in the coating gun. When the measured charge is 0.6 mA or more, the particulate material is rated as being good in chargeability. When the measured charge is less than 0.6 mA, then the particulate material is rated as being poor in chargeability.

The amount of the acrylic resin to be blended with the particulate material is preferably 0.1-1 % by weight based on the total weight of the acrylic resin and the particulate material.

Silica to be used as the charge controlling agent may be surface-treated or non-treated silica. Surface treatment of silica is performed so as to modify the silanol groups thereof with a trimethylsilyl group, aminosilyl group or the like group.

When silica is dispersed in water to form a slurry containing 5 % by weight of the silica, the slurry shows various pH values according to the type thereof. The silica whose slurry shows a pH of less than 7 is referred to as being "acidic" while the silica providing a pH of 7 or more is referred to as being "alkaline" in the present specification. Generally, non-treated silica is acidic because of the presence of silanol groups, while surface-treated silica is alkaline because the silanol groups have been modified.

It is preferred that alkaline silica or a mixture of alkaline silica and acidic silica be used in combination with the particulate material which is good in chargeability. In the case of the particulate material which is relatively poor in chargeability, then it is preferred that the particulate material be used in combination with acidic silica or a mixture of alkaline and acidic silica. The mixing ratio of the alkaline silica to the acidic silica is selected so as to obtain optimum results according to the chargeability of the particulate material.

The amount of the silica to be blended with the particulate material is preferably 0.01-1 % by weight, more preferably 0.05-0.1 % by weight based on the total weight of the



silica and the particulate material.

Second Embodiment

5 In the second embodiment according to the present invention, two, different, first and second charge controlling agents are used and are separately deposited on different particles of particulate material.

10 The particulate material described with reference to the above first embodiment may be used in the second embodiment. The particulate material on which the first charge controlling agent is to be deposited may be the same as or different from that on which the second charge controlling agent is to be deposited.

15 The charge controlling agent is fine powder (with a particle size of 1 μ m or less) of an organic or inorganic substance which is inert to the curing reaction of the epoxy resin and which has a polar group so that it can change the static characteristics of the particulate material when deposited on the particulate material. Illustrative of charge controlling agents are organic polymers containing oxygen, 20 nitrogen, sulfur or the like polar elements, inorganic oxides and metal salts. Especially suitable is the use of the acrylic resin or silica described with reference to the first embodiment.

25 The two, first and second charge controlling agents to be used in the present invention should differ in static characteristics from each other. The difference in chargeability results from various surface properties of the particles of the charge controlling agents, such as surface acidity and polarity. Such a difference in static 30 characteristics may be created by, for example, surface treating suitable organic or inorganic powder in two different manners. The surface treatment may be, for example, a heat treatment, a radiation treatment, a treatment with an acid or an alkali, a chemical modification treatment and an adsorption treatment. 35 More specifically, by treating a powder with an organic acid and by separately treating similar powder with an organic base,



there are obtained two charge controlling agents with different static characteristics (surface acidity). In this case, non-treated powder may be substituted for one of the acidic and alkaline charge controlling agents.

5 It is preferable to use a combination of first and second charge controlling agents showing pH of 7 or more and less than 7, respectively, when dispersed in water in an amount of 5 % by weight. Such first and second charge controlling agents are suitably formed of silica having unmodified silanol groups and treated silica having modified silanol groups, 10 respectively. It is also preferable to use a combination of first and second charge controlling agents which are positively and negatively charged, respectively, upon contact with iron powder. Such first and second charge controlling agents are 15 formed of acrylic resins. Thus, those charge controlling agents described above with reference to the first embodiment are suitably used in the second embodiment.

The coating composition according to the second embodiment may be obtained as follows. First, two particulate 20 materials A_1 and B_1 , which may be the same or different and each of which contains an epoxy resin and a curing agent are provided. Two particulate, charge controlling agents A_2 and B_2 are then dry mixed with the particulate materials A_1 and B_1 , respectively, to deposit the charge controlling agents A_2 and B_2 25 on the particulate materials A_1 and B_1 , respectively, thereby to obtain two kinds of mixtures A_3 and B_3 . The two mixtures A_3 and B_3 are blended with each other to obtain the powder coating composition of the present invention. The blending ratio $A_3:B_3$ is suitably 1:9 to 9:1, more preferably 3:7 to 7:3. The total 30 amount of A_2 and B_2 is generally in the range of 0.01-10 %, preferably 0.1-5 % based on the total weight of A_1 , B_1 , A_2 and B_2 .

The following examples will further illustrate the present invention.

35 Example 1

Powder coating compositions were prepared by dry

Particulate material:

5 EPIFOAM F-221 (manufactured by Somar Corporation)

Epoxy resin: diglycidyl ether of bisphenol A

Curing agent: dicyandiamide

Particle size: 80 mesh or finer

Volume resistivity: 5×10^{16} ohm·cm

10 Charge: 0.7 mA (good chargeability)

EPIFOAM F-220 (manufactured by Somar Corporation)

Epoxy resin: diglycidyl ether of bisphenol A

Curing agent: imidazole

15 Particle size: 80 mesh or finer

Volume resistivity: 3×10^{16} ohm-cm

Charge: 0.4 mA (poor chargeability)

Charge controlling agent:

20 Silica, CARPLEX FPS-3 (manufactured by Shionogi Inc.)

pH of 5 % Slurry: 7.5

Average particle size: about 15 nm (primary particles)

25 Silica, CARPLEX # 1120 (manufactured by Shionogi Inc.)

pH of 5 % Slurry: 10.7

Average particle size: about 15 nm (primary particles)

30 Silica, AEROSIL #300 (manufactured by Nihon Aerosil
Inc.)

pH of 5 % Slurry: 4

Average particle size: about 7 nm (primary particles)

35 Non-treated

Polymethyl methacrylate, MP-2701 (manufactured by Soken Kagaku K. K.)

Chargeability: positively charged upon contact
with iron

5 Particle size: 0.35-0.5 μm
Mw: 4×10^4 - 10×10^4

Polymethyl methacrylate, MP-1000 (manufactured by Soken Kagaku K. K.)

10 Chargeability: negatively charged upon contact
with iron

Particle size: 0.35-0.5 μm
Mw: 25×10^4 - 50×10^4

15 The thus prepared coating compositions were tested for
their performance in electrostatic coating. The tests are
performed as follows:

20 A motor armature having 10 slots each having a length
of 40 mm, a diameter of 29 mm and a width of 2 mm is coated with
a test sample coating composition using an electrostatic
fluidized bed coating apparatus for 30 seconds at a voltage of
50 KV with a fluidizing air atmosphere of 0.2 kg/cm². The
amount of the coating composition applied is measured. The
condition of the slots is observed to determine whether or not
25 the coating composition is got sufficiently into the the slots
to the depth thereof.

The results are summarized in Table 1.

This Sheet Has Been Replaced



Table 1

Experiment No.	1	2	3	4	5	6	7	8	9	10	11*	12*
Particulate Material												
EPIFOAM F-221	99.9	99.9	99.9			99.8	99.7	99.7			100	
EPIFOAM F-220				99.9	99.9				99.7	99.7		100
Silica												
CARPLEX FPS-3	0.1											
CARPLEX #1120		0.1	0.05		0.05							
AEROSIL #300			0.05	0.1	0.05							
Acrylic Resin												
MP-2701							0.3	0.2	0.3	0.1		
MP-1000						0.2		0.1		0.2		
Amount of Coating (g)	3.3	4.0	3.2	3.1	3.1	3.3	3.0	3.2	4.3	3.9	2.5	2.5
Condition of Coating in Slots	good	good	good	good	good	good	good	good	good	good	poor	poor

*: Comparative Sample

This Sheet Has Been Replaced





Example 2

The ingredients shown in Table 2 in proportions (% by weight) shown in Table 2 were blended to obtain mixtures A and B. Coating compositions were prepared by mixing the mixtures A and B with each other. The ingredients used are as follows:

Particulate material:

EPIFOAM F-221 (the same as used in Example 1)

Charge controlling agent:

Silica, CARPLEX # 1120 (the same as used in Example 1)

Silica, AEROSIL #300 (the same as used in Example 1)

Polymethyl methacrylate, MP-2701 (the same as used in Example 1)

Polymethyl methacrylate, MP-1000 (the same as used in Example 1)

Table 2

Experiment No.	13	14	15
Mixture A			
Particulate Material			
F-221	49.85	49.95	49.8
Charge Controlling agent			
Acrylic resin MP-2701	0.15		0.2
Silica #1120		0.05	
Mixture B			
Particulate Material			
F-221	49.85	49.95	49.9
Charge Controlling agent			
Acrylic resin MP-1000	0.15		0.1
Silica #300		0.05	
Amount of Coating (g)	4.3	4.1	4.9
Condition of Coating in Slots	good	good	good

Example 3

Experiments Nos. 11 and 15 were repeated in the same manner as described except that the coating time was changed to 60, 90, 120 and 150 seconds. The amount of the coating composition deposited to the armature was as shown in Table 3.

Table 3

Coating Time (seconds)	30	60	90	120	150
Amount of Coating (g)					
Experiment No. 15	4.9	7.0	7.8	8.8	9.9
Experiment No. 11*	2.5	3.4	3.8	4.0	4.1

*: Comparative Sample

This Sheet Has Been Replaced



WHAT IS CLAIMED IS

1. A powder coating composition comprising a particulate material consisting of particles having a particle size in the range of 3-180 μm and a volume resistivity of at least 10^7 ohm cm and each containing an epoxy resin and a curing agent for the epoxy resin, and a charge controlling agent selected from the group consisting of an acrylic resin having an average particle size in the range of 0.05-1 μm and silica whose primary particles having an average particle size in the range of 2-500 nm, the amount of said charge controlling agent being 0.01-5 % based on the total weight of said particulate material and said charge controlling agent, and said charge controlling agent being present on surfaces of said particles of said particulate material.

2. A powder coating composition comprising:

a first particulate material consisting of first particles having a particle size in the range of 3-180 μm and a volume resistivity of at least 10^7 ohm·cm and each containing a first epoxy resin and a first curing agent for the first epoxy resin;

a second particulate material consisting of second particles having a particle size in the range of 3-180 μm and a volume resistivity of at least 10^7 ohm·cm and each containing a second epoxy resin and a second curing agent for the second epoxy resin;

a first, particulate, charge controlling agent depositing on surfaces of said first particulate material; and

a second, particulate, charge controlling agent depositing on surfaces of said second particulate material, said first and second charge controlling agent differing in static characteristics from each other.

3. A composition according to claim 2, wherein the weight ratio of a total of said first particulate material and said first charge controlling agent to a total of said second particulate material and said second charge controlling agent is





5 in the range of 1:9 to 9:1.

4. A composition according to claim 2, wherein the total amount of said first and second controlling agents is in the range of 0.01-10 % based on the total weight of said first and second particulate materials and said first and second charge
5 controlling agents.

5. A composition according to claim 2, wherein said first particulate material is the same as said second particulate material.

6. A composition according to claim 2, wherein said first and second charge controlling agents show pH of 7 or more and less than 7, respectively, when dispersed in water in an amount of 5 % by weight.

7. A composition according to claim 6, wherein said first and second charge controlling agents are formed of silica having unmodified silanol groups and treated silica having modified silanol groups, respectively.

8. A composition according to claim 2, wherein said first and second charge controlling agents are positively and negatively charged, respectively, upon frictional contact with iron powder.

9. A composition according to claim 8, wherein said first and second charge controlling agents are formed of acrylic resins.



EPOXY POWDER COATING COMPOSITION
FOR USE IN ELECTROSTATIC COATING

Abstract

- 5 A powder coating composition is disclosed which includes a particulate material containing an epoxy resin and a curing agent, and fine powder of a charge controlling agent such as an acrylic resin, silica or a mixture thereof. The charge controlling agent is deposited on surfaces of the particles of the particulate material.

This Sheet Has Been Replaced



This Sheet Has Been Replaced



- 1 -

EPOXY POWDER COATING COMPOSITION FOR USE IN ELECTROSTATIC COATING

This invention relates to a powder coating composition suitable for use in electrostatic coating.

Electrostatic coating is now used in various fields because of a lot of advantages thereof such as easiness in
 5 controlling the thickness of coatings and absence of a step of preheating articles to be coated. Thus, a number of powder coating compositions are commercially available for use in electrostatic coating processes. Known powder coating
 10 compositions, however, has a problem because it is difficult to obtain thick coatings having a smooth surface. Namely, when a coating having a thickness of 250 μm or more is to be formed, particles of the coating composition cause electrostatic repelling so that the surface of the resulting coating becomes non-uniform.

15 The present invention has been made with the foregoing problem in conventional powder coating compositions in view. In accordance with one aspect of the present invention there is provided a powder coating composition comprising a particulate material consisting of particles having a particle size in the
 20 range of 3-180 μm and a volume resistivity of at least 10^7 ohm-cm and each containing an epoxy resin and a curing agent for the epoxy resin, and a charge controlling agent selected from the group consisting of an acrylic resin having an average particle size in the range of 0.05-1 μm and silica whose primary
 25 particles having an average particle size in the range of 2-500 nm, the amount of said charge controlling agent being 0.01-5 % based on the total weight of said particulate material and said charge controlling agent, and said charge controlling agent being present on surfaces of said particles of said particulate
 30 material.

In another aspect, the present invention provides a powder coating composition comprising:

a first particulate material consisting of first particles having a particle size in the range of 3-180 μm and a
 35 volume resistivity of at least 10^7 ohm-cm and each containing a first epoxy resin and a first curing agent for the first epoxy resin;

REPLACED SHEETS	SG
☒ Description : paged 1-6 to paged 7-11	
☒ Claim(s) : paged 1/2 to paged 1/2	
☐ Drawing(s) : paged to paged	
☐ Abstract : paged to paged	
DATE OF RECEIPT	

REPLACEMENT SHEETS	SG
☒ Description : paged 1-6 to paged 7-11	
☒ Claim(s) : paged 1/2 to paged 1/2	
☐ Drawing(s) : paged to paged	
☒ Abstract : paged 1/2 to paged 1/2	
DATE OF RECEIPT 30/8/96	



a second particulate material consisting of second particles having a particle size in the range of 3-180 μm and a volume resistivity of at least 10^7 ohm-cm and each containing a second epoxy resin and a second curing agent for the second epoxy resin;

a first, particulate, charge controlling agent depositing on surfaces of said first particulate material; and

a second, particulate, charge controlling agent depositing on surfaces of said second particulate material, said first and second charge controlling agent differing in static characteristics.

The present invention will now be described in detail below.


First Embodiment:

The powder coating composition of the first embodiment according to the present invention is composed of a particulate material consisting of particles having a particle size in the range of 3-180 μm and a volume resistivity of at least 10^7 ohm-cm. Each of the particles contains an epoxy resin and a curing agent for the epoxy resin.

Any conventionally used epoxy resin may be used in the present invention. Examples of suitable epoxy resins include glycidyl ethers of bisphenol A, bisphenol S, bisphenol F, phenol novolak resins and cresol novolak resins; glycidyl ester epoxy resins; glycidyl amino epoxy resins; cycloaliphatic epoxy resins; linear aliphatic epoxy resins; heterocyclic epoxy resins; and halogenated epoxy resins. These epoxy resins may be used singly or as a mixture of two or more. Epoxy resins which are solid at 20 ° C are generally used. But, it is possible to use the solid epoxy resins in conjunction with liquid epoxy resins as long as the mixed epoxy resins are solid at 20 ° C.

Conventional curing agents may be used for the above epoxy resins. Illustrative of suitable curing agents are aromatic amines, acid anhydrides, guanidine compounds, such as dicyandiamide, and imidazole compounds.

In addition to the epoxy resin and the curing agent,



the particulate material may further contain a filler, a pigment or the like conventional additive.

5 The particulate material is blended, in a dry state using, for example, a Henschel mixer or a Nauta mixer, with a charge controlling agent selected from an acrylic resin having an average particle size in the range of 0.05-1 μ m, preferably 0.15-0.6 μ m and silica whose primary particles having an average particle size in the range of 2-500 nm, preferably 5-100 nm so that the charge control agent deposits on the surface of the
10 particles of the particulate material. The amount of the charge controlling agent is 0.01-5 % based on the total weight of the particulate material and the charge controlling agent.

The acrylic resin to be used as the charge controlling agent is a homopolymer or a copolymer of an alkyl ester of
15 acrylic or methacrylic acid. Polymethyl methacrylates and polymethyl acrylates are examples of suitable acrylic resins.

When frictionally contacted with iron powder, acrylic resins are either positively or negatively charged. Both of the positively and negatively chargeable acrylic resins may be used
20 for the purpose of the present invention. In this case, it is preferred that the negatively chargeable acrylic resins or a mixture of the negatively chargeable and positively chargeable acrylic resins be used in combination with the particulate material which is good in chargeability. In the case of the
25 particulate material which is relatively poor in chargeability, then it is preferred that the particulate material be used in combination with the positively chargeable acrylic resins or a mixture of the positively chargeable and positively chargeable acrylic resins. The mixing ratio of the positively chargeable acrylic resin to the negatively chargeable acrylic resin is
30 selected so as to obtain optimum results according to the chargeability of the particulate material.

The ratings of "good" and "poor" in the chargeability of the particulate material are determined by as follows:
35 Sample particulate material is discharged through a nozzle of an electrostatic coating gun (Model AH-1 manufactured by Nordson Inc.) with an air pressure for discharging the particulate

This is the replacement sheet

Date: 30 AUG 1996



- 4 -

material of 1.5 kg/cm^2 and an air pressure for accelerating the particulate material of 3.5 kg/cm^2 while measuring the charge by means of a charge meter equipped in the coating gun. When the measured charge is 0.6 mA or more, the particulate material is rated as being good in chargeability. When the measured charge is less than 0.6 mA, then the particulate material is rated as being poor in chargeability.

The amount of the acrylic resin to be blended with the particulate material is preferably 0.1-1 % by weight based on the total weight of the acrylic resin and the particulate material.

Silica to be used as the charge controlling agent may be surface-treated or non-treated silica. Surface treatment of silica is performed so as to modify the silanol groups thereof with a trimethylsilyl group, aminosilyl group or the like group.

When silica is dispersed in water to form a slurry containing 5 % by weight of the silica, the slurry shows various pH values according to the type thereof. The silica whose slurry shows a pH of less than 7 is referred to as being "acidic" while the silica providing a pH of 7 or more is referred to as being "alkaline" in the present specification. Generally, non-treated silica is acidic because of the presence of silanol groups, while surface-treated silica is alkaline because the silanol groups have been modified.

It is preferred that alkaline silica or a mixture of alkaline silica and acidic silica be used in combination with the particulate material which is good in chargeability. In the case of the particulate material which is relatively poor in chargeability, then it is preferred that the particulate material be used in combination with acidic silica or a mixture of alkaline and acidic silica. The mixing ratio of the alkaline silica to the acidic silica is selected so as to obtain optimum results according to the chargeability of the particulate material.

The amount of the silica to be blended with the particulate material is preferably 0.01-1 % by weight, more preferably 0.05-0.1 % by weight based on the total weight of the

This is the replacement sheet

Date: 30 AUG 1996



silica and the particulate material.

Second Embodiment

5 In the second embodiment according to the present invention, two, different, first and second charge controlling agents are used and are separately deposited on different particles of particulate material.

10 The particulate material described with reference to the above first embodiment may be used in the second embodiment. The particulate material on which the first charge controlling agent is to be deposited may be the same as or different from that on which the second charge controlling agent is to be deposited.

15 The charge controlling agent is fine powder (with a particle size of 1 μ m or less) of an organic or inorganic substance which is inert to the curing reaction of the epoxy resin and which has a polar group so that it can change the static characteristics of the particulate material when deposited on the particulate material. Illustrative of charge controlling agents are organic polymers containing oxygen, 20 nitrogen, sulfur or the like polar elements, inorganic oxides and metal salts. Especially suitable is the use of the acrylic resin or silica described with reference to the first embodiment.

25 The two, first and second charge controlling agents to be used in the present invention should differ in static characteristics from each other. The difference in chargeability results from various surface properties of the particles of the charge controlling agents, such as surface acidity and polarity. Such a difference in static 30 characteristics may be created by, for example, surface treating suitable organic or inorganic powder in two different manners. The surface treatment may be, for example, a heat treatment, a radiation treatment, a treatment with an acid or an alkali, a chemical modification treatment and an adsorption treatment. 35 More specifically, by treating a powder with an organic acid and by separately treating similar powder with an organic base,

This is the replacement sheet

Date: 30 AUG 1996



there are obtained two charge controlling agents with different static characteristics (surface acidity). In this case, non-treated powder may be substituted for one of the acidic and alkaline charge controlling agents.

5 It is preferable to use a combination of first and second charge controlling agents showing pH of 7 or more and less than 7, respectively, when dispersed in water in an amount of 5 % by weight. Such first and second charge controlling agents are suitably formed of silica having unmodified silanol groups and treated silica having modified silanol groups, 10 respectively. It is also preferable to use a combination of first and second charge controlling agents which are positively and negatively charged, respectively, upon contact with iron powder. Such first and second charge controlling agents are 15 formed of acrylic resins. Thus, those charge controlling agents described above with reference to the first embodiment are suitably used in the second embodiment.

 The coating composition according to the second embodiment may be obtained as follows. First, two particulate 20 materials A_1 and B_1 , which may be the same or different and each of which contains an epoxy resin and a curing agent are provided. Two particulate, charge controlling agents A_2 and B_2 are then dry mixed with the particulate materials A_1 and B_1 , respectively, to deposit the charge controlling agents A_2 and B_2 25 on the particulate materials A_1 and B_1 , respectively, thereby to obtain two kinds of mixtures A_3 and B_3 . The two mixtures A_3 and B_3 are blended with each other to obtain the powder coating composition of the present invention. The blending ratio $A_3:B_3$ is suitably 1:9 to 9:1, more preferably 3:7 to 7:3. The total 30 amount of A_2 and B_2 is generally in the range of 0.01-10 %, preferably 0.1-5 % based on the total weight of A_1 , B_1 , A_2 and B_2 .

 The following examples will further illustrate the present invention.

35

Example 1

Powder coating compositions were prepared by dry

This is the replacement sheet

Date: 30 AUG 1996

5 EPIFOAM F-221 (manufactured by Somar Corporation)
Epoxy resin: diglycidyl ether of bisphenol A
Curing agent: dicyandiamide
Particle size: 80 mesh or finer
Volume resistivity: 5×10^{16} ohm-cm
10 Charge: 0.7 mA (good chargeability)

15 EPIFOAM F-220 (manufactured by Somar Corporation)
Epoxy resin: diglycidyl ether of bisphenol A
Curing agent: imidazole
Particle size: 80 mesh or finer
Volume resistivity: 3×10^{16} ohm-cm
Charge: 0.4 mA (poor chargeability)

20	Silica, CARPLEX FPS-3 (manufactured by Shionogi Inc.) pH of 5 % Slurry: 7.5 Average particle size: about 15 nm (primary particles)
25	Silica, CARPLEX # 1120 (manufactured by Shionogi Inc.) pH of 5 % Slurry: 10.7 Average particle size: about 15 nm (primary particles)
30	Silica, AEROSIL #300 (manufactured by Nihon Aerosil Inc.) pH of 5 % Slurry: 4 Average particle size: about 7 nm (primary particles)
35	Non-treated

This is the replacement sheet

30 AUG 1956

Date:

Polymethyl methacrylate, MP-2701 (manufactured by Soken Kagaku K. K.)

Chargeability: positively charged upon contact
with iron

5 Particle size: 0.35-0.5 μ m
Mw: 4×10^4 - 10×10^4

Polymethyl methacrylate, MP-1000 (manufactured by Soken Kagaku K. K.)

10 Chargeability: negatively charged upon contact
with iron

Particle size: 0.35-0.5 μ m
Mw: 25×10^4 - 50×10^4

15 The thus prepared coating compositions were tested for
their performance in electrostatic coating. The tests are
performed as follows:

20 A motor armature having 10 slots each having a length
of 40 mm, a diameter of 29 mm and a width of 2 mm is coated with
a test sample coating composition using an electrostatic
fluidized bed coating apparatus for 30 seconds at a voltage of
50 KV with a fluidizing air atmosphere of 0.2 kg/cm². The
amount of the coating composition applied is measured. The
condition of the slots is observed to determine whether or not
25 the coating composition is got sufficiently into the the slots
to the depth thereof.

The results are summarized in Table 1.

This is the replacement sheet

Date: 30 AUG 1996

Table 1

Experiment No.	1	2	3	4	5	6	7	8	9	10	11*	12*
Particulate Material												
EPIFOAM F-221	99.9	99.9	99.9			99.8	99.7	99.7			100	
EPIFOAM F-220				99.9	99.9				99.7	99.7		100
Silica												
CARPLEX FPS-3	0.1											
CARPLEX #1120		0.1	0.05		0.05							
AEROSIL #300			0.05	0.1	0.05							
Acrylic Resin												
MP-2701							0.3	0.2	0.3	0.1		
MP-1000						0.2		0.1		0.2		
Amount of Coating (g)	3.3	4.0	3.2	3.1	3.1	3.3	3.0	3.2	4.3	3.9	2.5	2.5
Condition of Coating in Slots	good	good	good	good	good	good	good	good	good	good	poor	poor

*: Comparative sample

This is the replacement sheet

Date: 30 AUG 1996

Example 2

The ingredients shown in Table 2 in proportions (% by weight) shown in Table 2 were blended to obtain mixtures A and B. Coating compositions were prepared by mixing the mixtures A and B with each other. The ingredients used are as follows:

Particulate material:

EPIFOAM F-221 (the same as used in Example 1)

Charge controlling agent:

Silica, CARPLEX # 1120 (the same as used in Example 1)

Silica, AEROSIL #300 (the same as used in Example 1)

Polymethyl methacrylate, MP-2701 (the same as used in Example 1)

Polymethyl methacrylate, MP-1000 (the same as used in Example 1)

Table 2

Experiment No.	13	14	15
Mixture A			
Particulate Material			
F-221	49.85	49.95	49.8
Charge Controlling agent			
Acrylic resin MP-2701	0.15		0.2
Silica #1120		0.05	
Mixture B			
Particulate Material			
F-221	49.85	49.95	49.9
Charge Controlling agent			
Acrylic resin MP-1000	0.15		0.1
Silica #300		0.05	
Amount of Coating (g)	4.3	4.1	4.9
Condition of Coating in Slots	good	good	good

This is the replacement sheet

Date: 30 AUG 1996

Example 3

Experiments Nos. 11 and 15 were repeated in the same manner as described except that the coating time was changed to 60, 90, 120 and 150 seconds. The amount of the coating composition deposited to the armature was as shown in Table 3.

Table 3

Coating Time (seconds)	30	60	90	120	150
Amount of Coating (g)					
Experiment No. 15	4.9	7.0	7.8	8.8	9.9
Experiment No. 11*	2.5	3.4	3.8	4.0	4.1

*: Comparative Sample

This is the replacement sheet

Date: 30 AUG 1986



- 1 -

WHAT IS CLAIMED IS

1. A powder coating composition comprising a particulate material consisting of particles having a particle size in the range of 3-180 μm and a volume resistivity of at least 10^7 ohm cm and each containing an epoxy resin and a curing agent for the epoxy resin, and a charge controlling agent selected from the group consisting of an acrylic resin having an average particle size in the range of 0.05-1 μm and silica whose primary particles having an average particle size in the range of 2-500 nm, the amount of said charge controlling agent being 0.01-5 % based on the total weight of said particulate material and said charge controlling agent, and said charge controlling agent being present on surfaces of said particles of said particulate material.
2. A powder coating composition comprising:
a first particulate material consisting of first particles having a particle size in the range of 3-180 μm and a volume resistivity of at least 10^7 ohm-cm and each containing a first epoxy resin and a first curing agent for the first epoxy resin;
a second particulate material consisting of second particles having a particle size in the range of 3-180 μm and a volume resistivity of at least 10^7 ohm-cm and each containing a second epoxy resin and a second curing agent for the second epoxy resin;
a first, particulate, charge controlling agent depositing on surfaces of said first particulate material; and
a second, particulate, charge controlling agent depositing on surfaces of said second particulate material, said first and second charge controlling agent differing in static characteristics from each other.
3. A composition according to claim 2, wherein the weight ratio of a total of said first particulate material and said first charge controlling agent to a total of said second particulate material and said second charge controlling agent is



* C L M S *

This is the replacement sheet

Date:

30 AUG 1996



5 in the range of 1:9 to 9:1.

4. A composition according to claim 2, wherein the total amount of said first and second controlling agents is in the range of 0.01-10 % based on the total weight of said first and second particulate materials and said first and second charge controlling agents.

5. A composition according to claim 2, wherein said first particulate material is the same as said second particulate material.

6. A composition according to claim 2, wherein said first and second charge controlling agents show pH of 7 or more and less than 7, respectively, when dispersed in water in an amount of 5 % by weight.

7. A composition according to claim 6, wherein said first and second charge controlling agents are formed of silica having unmodified silanol groups and treated silica having modified silanol groups, respectively.

8. A composition according to claim 2, wherein said first and second charge controlling agents are positively and negatively charged, respectively, upon frictional contact with iron powder.

9. A composition according to claim 8, wherein said first and second charge controlling agents are formed of acrylic resins.



This is the replacement sheet

Date: 30 AUG 1996

EPOXY POWDER COATING COMPOSITION
FOR USE IN ELECTROSTATIC COATING

Abstract

5 A powder coating composition is disclosed which includes a particulate material containing an epoxy resin and a curing agent, and fine powder of a charge controlling agent such as an acrylic resin, silica or a mixture thereof. The charge controlling agent is deposited on surfaces of the particles of the particulate material.

This is the replacement sheet

Date: 30 AUG 1996

REPLACED SHEETS	SG
☒ Description : paged to paged	
☒ Claim(s) : paged to paged	
☐ Drawing(s) : paged to paged	
☐ Abstract : paged to paged	
DATE OF RECEIPT	

- 1 -

REPLACEMENT SHEETS	SG
☒ Description : paged ^{14, 24} to paged	
☒ Claim(s) : paged ¹⁴ to paged ¹⁴	
☐ Drawing(s) : paged to paged	
☐ Abstract : paged to paged	
DATE OF RECEIPT ^{27/11/97}	

Epoxy Powder Coating Composition For Use In Electrostatic Coating

This invention relates to a powder coating composition suitable for use in electrostatic coating.

Electrostatic coating is now used in various fields because it has a lot of advantages, such as easiness in controlling the thickness of coatings and absence of a step of preheating articles to be coated. Thus, a number of powder coating compositions are commercially available for use in electrostatic coating processes. Known powder coating compositions, however, have a problem that it is difficult to obtain thick coatings having a smooth surface. Namely, when a coating having a thickness of 250 μm or more is to be formed, particles of the coating composition cause electrostatic repelling so that the surface of the resulting coating becomes non-uniform.

The present invention has been made with the foregoing problem in conventional powder coating compositions in view.

EP-A-0389080 discloses powder coating compositions which comprise particles of a thermoplastic or thermosetting resin carrying at least on the surface thereof microparticles of such a resin having specified glass transition temperature and solubility characteristics. Examples are given where the substrate resin is an epoxy resin and the microparticulate coating thereon is formed of an acrylic resin.

JP-A-1168772 discloses powder coating compositions which comprise a mixture of an epoxy resin, a phenolic curing agent and finely divided, substantially anhydrous silica.

In accordance with a first embodiment of the present invention there is provided a powder coating composition comprising a particulate material consisting of particles having a particle size in the range of 3-180 μm and a volume resistivity of at least 10^7 ohm.cm and each containing an epoxy resin and a curing agent for

This is the replacement sheet

Date: 27 NOV 1997

the epoxy resin, and as a charge controlling agent an acrylic resin having an average particle size in the range of 0.05-1 μm and being present on surfaces of said particles of said particulate material, the amount of said acrylic resin being 0.01-5% by weight based on the total weight of said particulate material and said acrylic resin, and

(a) when said particulate material has a chargeability of at least 0.6 mA (as determined by the Test defined below), then said acrylic resin is negatively chargeable upon frictional contact with iron powder; or

(b) when said particulate material has a chargeability of less than 0.6 mA (as determined by the Test defined below), then said acrylic resin is positively chargeable upon frictional contact with iron powder:

Test for Determining Chargeability

Discharge sample of particulate material through nozzle of an electrostatic coating gun (Model AH-a manufactured by Nordson Inc., USA) with an air pressure for discharging the particulate material of 1.5 kg/cm² and an air pressure for accelerating the particulate material of 3.5 kg/cm² while measuring the charge by means of a charge meter with which the coating gun is equipped.

In accordance with a second embodiment, the present invention provides a powder coating composition comprising:

a first particulate material consisting of first particles having a particle size in the range of 3-180 μm and a volume resistivity of at least 10^7 ohm.cm and each containing a first epoxy resin and a first curing agent for the first epoxy resin;

This is the replacement sheet

Date: 27 NOV 1997

a second particulate material consisting of second particles having a particle size in the range of 3-180 μm and a volume resistivity of at least 10^7 ohm-cm and each containing a second epoxy resin and a second curing agent for the second epoxy resin;

a first, particulate, charge controlling agent depositing on surfaces of said first particulate material; and

a second, particulate, charge controlling agent depositing on surfaces of said second particulate material, said first and second charge controlling agent differing in static characteristics.

The present invention will now be described in detail below.

First Embodiment:

The powder coating composition of the first embodiment according to the present invention is composed of a particulate material consisting of particles having a particle size in the range of 3-180 μm and a volume resistivity of at least 10^7 ohm-cm. Each of the particles contains an epoxy resin and a curing agent for the epoxy resin.

Any conventionally used epoxy resin may be used in the present invention. Examples of suitable epoxy resins include glycidyl ethers of bisphenol A, bisphenol S, bisphenol F, phenol novolak resins and cresol novolak resins; glycidyl ester epoxy resins; glycidyl amino epoxy resins; cycloaliphatic epoxy resins; linear aliphatic epoxy resins; heterocyclic epoxy resins; and halogenated epoxy resins. These epoxy resins may be used singly or as a mixture of two or more. Epoxy resins which are solid at 20 ° C are generally used, but, it is possible to use the solid epoxy resins in conjunction with liquid epoxy resins as long as the mixed epoxy resins are solid at 20 ° C.

Conventional curing agents may be used for the above epoxy resins. Illustrative of suitable curing agents are aromatic amines, acid anhydrides, guanidine compounds such as dicyandiamide, and imidazole compounds.

In addition to the epoxy resin and the curing agent,

This is the replacement sheet

Date: 27 NOV 1997

the particulate material may further contain a filler, a pigment or the like conventional additive.

The particulate material is blended, in a dry state using, for example, a Henschel mixer or a Nauta mixer, with a charge controlling agent which is an acrylic resin having an average particle size in the range of 0.05-1 μm , preferably 0.15-0.6 μm , so that the charge control agent deposits on the surface of the particles of the particulate material. The amount of the charge controlling agent is 0.01-5 % based on the total weight of the particulate material and the charge controlling agent.

The acrylic resin to be used as the charge controlling agent is a homopolymer or a copolymer of an alkyl ester of acrylic or methacrylic acid. Polymethyl methacrylates and polymethyl acrylates are examples of suitable acrylic resins.

When frictionally contacted with iron powder, acrylic resins are either positively or negatively charged. Both of the positively and negatively chargeable acrylic resins may be used for the purpose of the present invention. In this case, it is required that negatively chargeable acrylic resins or a mixture of negatively chargeable and positively chargeable acrylic resins be used in combination with particulate material which is good in chargeability. In the case of the particulate material which is relatively poor in chargeability, then it is required that the particulate material be used in combination with positively chargeable acrylic resins or a mixture of the positively chargeable and positively chargeable acrylic resins. The mixing ratio of the positively chargeable acrylic resin to the negatively chargeable acrylic resin is selected so as to obtain optimum results according to the chargeability of the particulate material.

The ratings of "good" and "poor" in the chargeability of the particulate material are determined by as follows: Sample particulate material is discharged through a nozzle of an electrostatic coating gun (Model AH-1 manufactured by Nordson Inc.) with an air pressure for discharging the particulate

This is the replacement sheet

Date: 27 NOV 1997

material of 1.5 kg/cm^2 and an air pressure for accelerating the particulate material of 3.5 kg/cm^2 while measuring the charge by means of a charge meter equipped in the coating gun. When the measured charge is 0.6 mA or more, the particulate material is rated as being good in chargeability. When the measured charge is less than 0.6 mA, then the particulate material is rated as being poor in chargeability.

The amount of the acrylic resin to be blended with the particulate material is preferably 0.1-1 % by weight based on the total weight of the acrylic resin and the particulate material.

This is the replacement sheet

Date: 27 NOV 1997

Second Embodiment

In the second embodiment according to the present invention, two, different, first and second charge controlling agents are used and are separately deposited on different particles of particulate material.

The particulate material described above with reference to the first embodiment may be used in the second embodiment. The particulate material on which the first charge controlling agent is to be deposited may be the same as or different from that on which the second charge controlling agent is to be deposited.

The charge controlling agent is fine powder (with a particle size of 1 μm or less) of an organic or inorganic substance which is inert to the curing reaction of the epoxy resin and which has a polar group so that it can change the static characteristics of the particulate material when deposited on the particulate material. Illustrative of charge controlling agents are organic polymers containing oxygen, nitrogen, sulfur or the like polar elements, inorganic oxides and metal salts. Especially suitable is the use of the acrylic resin described with reference to the first embodiment, or silica whose primary particles have an average particle size in the range of 2-500 nm, preferably 5-100 nm.

The two, first and second charge controlling agents to be used in the present invention should differ in static characteristics from each other. The difference in chargeability results from various surface properties of the particles of the charge controlling agents, such as surface acidity and polarity. Such a difference in static characteristics may be created by, for example, surface treating suitable organic or inorganic powder in two different manners. The surface treatment may be, for example, a heat treatment, a radiation treatment, a treatment with an acid or an alkali, a chemical modification treatment and an adsorption treatment. More specifically, by treating a powder with an organic acid and by separately treating similar powder with an organic base,

This is the replacement sheet

Date: 27 NOV 1997

there are obtained two charge controlling agents with different static characteristics (surface acidity). In this case, non-treated powder may be substituted for one of the acidic and alkaline charge controlling agents.

It is preferable to use a combination of first and second charge controlling agents showing pH of 7 or more and less than 7, respectively, when dispersed in water in an amount of 5 % by weight. Such first and second charge controlling agents are suitably formed, respectively, of silica having modified silanol groups for example modified with trimethylsilyl groups or aminosilyl groups and silica having unmodified silanol groups. It is also preferable to use a combination of first and second charge controlling agents which are positively and negatively charged, respectively, upon contact with iron powder. Such first and second charge controlling agents are formed of acrylic resins, as described above with reference to the first embodiment.

The coating composition according to the second embodiment may be obtained as follows. First, two particulate materials A_1 and B_1 , which may be the same or different and each of which contains an epoxy resin and a curing agent are provided. Two particulate, charge controlling agents A_2 and B_2 are then dry mixed with the particulate materials A_1 and B_1 , respectively, to deposit the charge controlling agents A_2 and B_2 on the particulate materials A_1 and B_1 , respectively, thereby to obtain two kinds of mixtures A_3 and B_3 . The two mixtures A_3 and B_3 are blended with each other to obtain the powder coating composition of the present invention. The blending ratio $A_3:B_3$ is suitably 1:9 to 9:1, more preferably 3:7 to 7:3. The total amount of A_2 and B_2 is generally in the range of 0.01-10 %, preferably 0.1-5 % based on the total weight of A_1 , B_1 , A_2 and B_2 .

The following examples will further illustrate the present invention.

Example 1

Powder coating compositions were prepared by dry

This is the replacement sheet

Date: 27 NOV 1997

CLAIMS:

1. A powder coating composition comprising a particulate material consisting of particles having a particle size in the range of 3-180 μm and a volume resistivity of at least 10^7 ohm.cm and each containing an epoxy resin and a curing agent for the epoxy resin, and as a charge controlling agent an acrylic resin having an average particle size in the range of 0.05-1 μm and being present on surfaces of said particles of said particulate material, the amount of said acrylic resin being 0.01-5% by weight based on the total weight of said particulate material and said acrylic resin, and

(a) when said particulate material has a chargeability of at least 0.6 mA (as determined by the Test defined below), then said acrylic resin is negatively chargeable upon frictional contact with iron powder; or

(b) when said particulate material has a chargeability of less than 0.6 mA (as determined by the Test defined below), then said acrylic resin is positively chargeable upon frictional contact with iron powder:

Test for Determining Chargeability

Discharge sample of particulate material through nozzle of an electrostatic coating gun (Model AH-1 manufactured by Nordson Inc., USA) with an air pressure for discharging the particulate material of 1.5 kg/cm² and an air pressure for accelerating the particulate material of 3.5 kg/cm² while measuring the charge by means of a charge meter with which the coating gun is equipped.

This is the replacement sheet



Date: 27 NOV 1997

2. A composition according to Claim 1, wherein said acrylic resin has a particle size in the range of 0.15-0.6 μm .

3. A composition according to Claim 1 or Claim 2, wherein said amount of said acrylic resin is 0.1-1% by weight.

4. A powder coating composition comprising:

a first particulate material consisting of first particles having a particle size in the range of 3-180 μm and a volume resistivity of at least 10^7 ohm.cm and each containing a first epoxy resin and a first curing agent for the first epoxy resin;

a second particulate material consisting of second particles having a particle size in the range of 3-180 μm and a volume resistivity of at least 10^7 ohm.cm and each containing a second epoxy resin and a second curing agent for the second epoxy resin;

a first, particulate, charge controlling agent depositing on surfaces of said first particulate material; and

a second, particulate, charge controlling agent depositing on surfaces of said second particulate material, said first and second charge controlling agent differing in static characteristics from each other.

5. A composition according to Claim 4, wherein the weight ratio of the total of said first particulate material and said first charge controlling agent to the total of said second particulate material and said second charge controlling agent is in the range of 1:9 to 9:1.

This is the replacement sheet



Date: 27 NOV 1997

6. A composition according to Claim 4 or Claim 5, wherein the total amount of said first and second controlling agents is in the range of 0.01-10% based on the total weight of said first and second particulate materials and said first and second charge controlling agents.
7. A composition according to any one of Claims 4-6, wherein said first particulate material is the same as said second particulate material.
8. A composition according to any one of Claims 4-7, wherein said first and second charge controlling agents exhibit a pH of 7 or more and less than 7, respectively, when dispersed in water in an amount of 5% by weight.
9. A composition according to Claim 8, wherein said first charge controlling agent is formed of treated silica having modified silanol groups and said second charge controlling agent is formed of silica having unmodified silanol groups, respectively.
10. A composition according to any one of Claims 4-7, wherein said first and second charge controlling agents are formed of acrylic resins.
11. A composition according to Claim 10, wherein said first and second charge controlling agents are positively and negatively charged, respectively, upon frictional contact with iron powder.



This is the replacement sheet

Date:

27 NOV 1997